


ANISOTROPIC RUBBER MAGNET

MODEL	DIM.	A / $\begin{smallmatrix} +0.00 \\ -0.80 \end{smallmatrix}$	B / $\begin{smallmatrix} +0.80 \\ -0.00 \end{smallmatrix}$	C / ± 0.2
ME - 16 - 8 × 4		15.50	8.00	4.00
ME - 20 - 9 × 4		19.50	9.00	4.00
ME - 25 - 13 × 4		24.50	13.00	4.00
ME - 30 - 21 × 4		29.50	21.00	4.00
ME - 32 - 21 × 4		31.50	21.00	4.00
ME - 40 - 22 × 4		39.50	22.00	4.00
ME - 50 - 32 × 4		49.50	32.00	4.00
ME - 63 - 42 × 4		62.50	42.00	4.00
ME - 80 - 58 × 4		79.50	58.00	4.00
ME - 100 - 78 × 4		99.50	78.00	4.00
ME - 125 - 79 × 4		124.50	79.00	4.00
ME - 125 - 108 × 4		124.50	108.00	4.00
ME - 150 - 125 × 4		149.50	125.00	4.00
ME - 200 - 176 × 4		195.50	176.00	4.00

MODEL	DIM.	A / $\begin{smallmatrix} +0.00 \\ -0.80 \end{smallmatrix}$	B / $\begin{smallmatrix} +0.80 \\ -0.00 \end{smallmatrix}$	C / ± 0.2
ME - 16 - 8 × 5		15.50	8.00	5.00
ME - 20 - 9 × 5		19.50	9.00	5.00
ME - 25 - 13 × 5		24.50	13.00	5.00
ME - 30 - 21 × 5		29.50	21.00	5.00
ME - 32 - 21 × 5		31.50	21.00	5.00
ME - 40 - 22 × 5		39.50	22.00	5.00
ME - 50 - 32 × 5		49.50	32.00	5.00
ME - 63 - 42 × 5		62.50	42.00	5.00
ME - 80 - 58 × 5		79.50	58.00	5.00
ME - 100 - 78 × 5		99.50	78.00	5.00



CHARACTERISTIC

A. Magnetic property:

Residual flux density (Br): 2300 - 2500 gauss
 Coercive force (iHC): 3000 - 3800 Oe
 (bHC): 2000 - 2300 Oe
 Maximum energy product: 1.3 - 1.5 Mg.Oe


B. Physical property:

Resistant power: 20 - 50 kgf/cm²
 Lengthen: 5 - 20 %
 Hardness (Shore D): 30 - 50
 Specific gravity: 3.5 - 3.7 g/cm³
 Temperature range: -20°C ~ +70°C

ANISOTROPIC PLASTIC MAGNET

MODEL	DIM.	A / \pm	B / $\begin{smallmatrix} +0.30 \\ -0.00 \end{smallmatrix}$	C / ± 0.2
PME - 20 - 9 × 4		19.50	9.00	4.00
PME - 25 - 13 × 4		24.50	13.00	4.00
PME - 30 - 21 × 4		29.50	21.00	4.00
PME - 32 - 21 × 4		31.50	21.00	4.00
PME - 40 - 22 × 4		39.50	22.00	4.00
PME - 50 - 32 × 4		49.50	32.00	4.00
PME - 63 - 42 × 4		62.50	42.00	4.00
PME - 80 - 58 × 4		79.50	58.00	4.00
PME - 100 - 78 × 4		99.50	78.00	4.00

MODEL	DIM.	A / $\begin{smallmatrix} +0.00 \\ -0.30 \end{smallmatrix}$	B / $\begin{smallmatrix} +0.30 \\ -0.00 \end{smallmatrix}$	C / ± 0.2
PME - 12 - 6 × 5		11.50	6.00	5.00
PME - 16 - 8 × 5		15.50	8.00	5.00
PME - 20 - 9 × 5		19.50	9.00	5.00
PME - 25 - 13 × 5		24.50	13.00	5.00
PME - 30 - 21 × 5		29.50	21.00	5.00
PME - 32 - 21 × 5		31.50	21.00	5.00
PME - 40 - 22 × 5		39.50	22.00	5.00
PME - 50 - 32 × 5		49.50	32.00	5.00
PME - 63 - 42 × 5		62.50	42.00	5.00
PME - 80 - 58 × 5		79.50	58.00	5.00
PME - 100 - 78 × 5		99.50	78.00	5.00



CHARACTERISTIC

A. Magnetic property:

Residual flux density (Br): 2500 - 3000 gauss
 Coercive force (iHC): 2700 - 3100 Oe
 (bHC): 2400 - 2500 Oe
 Maximum energy product: 1.8 Mg.Oe

B. Physical property:

Resistant power: 80 kgf/cm²
 Lengthen: 6.7 %
 Hardness (Shore D): 120
 Specific gravity: 3.2 g/cm³
 Temperature range: -20°C ~ +100°C